

Test laboratory for the fire behavior of building materials, Dipl.-Ing. (FH) Andreas Hoch
Testing, supervising and certifying body, authorized by the building supervision authority

TEST REPORT

PZ-Hoch-171361

for the proof of Fire behaviour according to DIN 4102, part 1

Translation of the German test report – no guarantee for translation of technical terms

company	Artimo Textiles BV De Meeten 53 4706 NK Roosendaal The Netherlands
description of samples	fabric consisting of 100% Polyester in 3 different colours
name of the material	BERGA
sampling	by the company itself
content of request	Proof of flammability to classify building materials to class B1 "schwerentflammbar" according to DIN 4102, part 1
validity of test report	31.10.2022
result	The examined product meets in any colour the requirements of class B1 for "schwerentflammbare" (hardly flammable) building materials according to DIN 4102, part 1 (May 1998), suspended freely or with distance of >40 mm to same or other plain materials.

This test report includes 5 pages and 6 enclosures.

Remark: If the above mentioned building material is not used as product according to MBO § 2, Abs. 9, Ziffer 1, there is no need for a general building supervisory test report.

This test report is not valid if the examined building material is used as product in the meaning of state building prescriptions (MBO § 17, Abs. 3).

This test report does not replace an eventually necessary proof of applicability concerning building supervisory or building laws in the meaning of state building prescriptions. This has to be verified by:

- "allgemeine bauaufsichtliche Zulassung" (general building inspectorate approval) or by
- „allgemeines bauaufsichtliches Prüfzeugnis" (general building inspectorate certificate) or by
- "Zustimmung im Einzelfall" (exceptional approval)

This test report can underlie building supervisory procedures

- for regular building products for the prescribed proofs of conformity
- for non-regular building products for the needed proofs of applicability.

This test report must not be published and copied without preceding agreement of the test laboratory and if agreed, only during validity and unchanged concerning appearance and contents.

1. Description of test material in condition as delivered

PN 26478: BERGA colour: white
-fabric consisting of 100% Polyester-
There is no difference between side A and side B.
characteristic values determined by the test laboratory:
area weight: about 245 g/m² thickness: about 0,67 mm

PN 26479: BERGA colour: beige-red
-fabric consisting of 100% Polyester-
There is no difference between side A and side B.
characteristic values determined by the test laboratory:
area weight: about 197 g/m² thickness: about 0,70 mm

PN 26480: BERGA colour: grey
-fabric consisting of 100% Polyester-
There is no difference between side A and side B.
characteristic values determined by the test laboratory:
area weight: about 196 g/m² thickness: about 0,68 mm

The testing laboratory is not provided with further details concerning composition of the tested building materials. Samples are deposited.

2. Preparation of samples

The samples were kept in climate chamber 23/50 until they reached constant weight.

3. Arrangement of samples mounting: freely suspended

#9709:	flaming side A in warp direction	white
#9710:	flaming side B in weft direction	white
#9711:	flaming side A in warp direction	beige-red
#9712:	flaming side A in warp direction	grey

4. Date of test CW 48 in 2017

5. **Results** The test has been examined according to DIN 4102 (Mai 1998)

line no.	Measurement	Result with the tested specimen				Dim.
	Test number	#9709	#9710	#9711	#9712	
	flaming direction / side	warp / A	weft / B	warp / A	warp / A	
	colour of fabric	white		beige-red	grey	
1	Number of specimen arrangement acc. to. DIN 4102/T15, schedule 1	1	1	1	1	
2	Maximum flame height above bottom edge of the specimen	30	30	30	30	cm
3	Time ¹⁾	0:02	0:02	0:02	0:02	min:s
4	Burn through / melting Time ¹⁾	0:05	0:06	0:05	0:05	min:s
5	Observations on the back side of the specimen Flames / Glowing Time ¹⁾	./.	./.	./.	./.	min:s
6	Change of colour Time ¹⁾	./.	./.	./.	./.	min:s
7	Falling of burning droplets Start ¹⁾	./.	./.	./.	./.	min:s
8	Extent sporadic falling of burning droplets ²⁾	./.	./.	./.	./.	min:s
9	continuous falling of burning droplets ²⁾	./.	./.	./.	./.	
10	Falling of burning droplets Start ¹⁾	./.	./.	./.	./.	min:s
11	Extent sporadic falling of burning droplets ²⁾	./.	./.	./.	./.	
12	continuous falling of burning droplets ²⁾	./.	./.	./.	./.	
13	After flame time at the bottom of the sieve (max.)	./.	./.	./.	./.	min:s
14	Impairment of the burner by dropping or falling material: Time ¹⁾	./.	./.	./.	./.	min:s
15	Premature end of test Final occurrence of burning at the specimen ¹⁾	./.	./.	./.	./.	min:s
16	Time of eventually end of test ¹⁾	./.	./.	./.	./.	min:s
17	After flame after end of test Time ¹⁾	./.	./.	./.	./.	min:s
18	Number of specimen	./.	./.	./.	./.	cm
19	Front side of specimen ²⁾	./.	./.	./.	./.	
20	Back side of specimen ²⁾	./.	./.	./.	./.	
21	flame length	./.	./.	./.	./.	

No.	Measurement	Result with the tested specimen				Dim.
		#9709	#9710	#9711	#9712	
	Test number					
	flaming direction / side	warp / A	weft / B	warp / A	warp / A	
	<u>Afterglow after end of test</u>	./.	./.	./.	./.	min:s
22	Time ¹⁾	./.	./.	./.	./.	
23	Number of specimen	./.	./.	./.	./.	
	<u>Place of appearance</u>	./.	./.	./.	./.	
24	Lower half of the specimen ²⁾	./.	./.	./.	./.	
25	Upper half of the specimen ²⁾	./.	./.	./.	./.	
26	Front side of specimen ²⁾	./.	./.	./.	./.	
27	Back side of specimen ²⁾	./.	./.	./.	./.	
	<u>Density of smoke</u>					
28	≤ 400 % * min	1	1	1	1	% * min
29	> 400 % * min ⁴⁾	./.	./.	./.	./.	% * min
30	Diagram: incl. no.	1	2	3	4	
	<u>Residual lengths: individual value³⁾</u>					
31	Specimen 1	69	68	63	67	cm
	Specimen 2	68	68	56	68	cm
	Specimen 3	62	66	64	65	cm
	Specimen 4	67	70	59	65	cm
32	<u>Average value, individual test ³⁾</u>	67	68	61	66	
33	<u>Photo of specimen in enclosure no.</u>	1	2	3	4	
34	<u>Flue gas temperature</u>	122	122	123	124	°C
35	Maximum of average value Time ¹⁾	10:00	09:24	09:51	09:02	min:s
36	Diagram: incl. no.	1	2	3	4	
37	Remarks: - none -					

¹⁾ indication of times: from the begin of testing procedure ²⁾ checked off if applicable

³⁾ indication of carrier/foam layer separated in case of fire-proofing agents

⁴⁾ very strong development of smoke

6. Explanations concerning the testing procedure

There were no additional tests proceeded because of the residual length of more than 45 cm.

7. Summary of results and additional establishments to Fire Behaviour

lineo.	measurement	Result with the tested specimen				dimension
	test-no.	#9709 warp / A	#9710 weft / B	#9711 warp / A	#9712 warp / A	
	<u>colour of fabric</u>	white		beige-red	grey	
1	residual length	67	68	61	66	cm
2	max. smoke temperature	122	122	123	124	°C
3	density of smoke - integral	1	1	1	1	%min
4	remarks: -none-					

According to DIN 4102, part 1, "schwerentflammbare" (hardly flammable) building materials must meet the requirements of class B2.

Pursuant to additional tests in the ignitability apparatus this can be determined (appendix 5 & 6).

8. Special remarks


- This report is only valid for the material as described under paragraph 1. In combination with other materials or with additional coatings or grounds etc. the burning behaviour may differ.
- This test report is not valid for the exposure to outdoor climate conditions, washing or cleaning with chemicals, washing or cleaning with chemicals.
- This test report is not valid, as soon as the fabric is used as a building product in the sense of the "Landesbauordnungen" (state building requirements, MBO § 17, par. 3).
- This test report is no substitute for a General Building Inspectorate Certificate.
- This test report is granted without prejudice to the rights of third parties, in particular private proprietary rights.
- For legal interests only the German original version is relevant.
- In General Building Inspectorates procedures this test report can be based for
 - regular building materials for the required proof of accordance
 - for not regular building materials for the required proof of applicability

9. Validity

This test report is valid until the mentioned date on page 1. The test report becomes invalid in case the standards on which the tests are based are changed.

Fladungen, 04.12.2017

clerk in charge:



(Dipl.-Ing. (FH) Jürgen Hammer)



Head of the test laboratory:



(Dipl.-Ing. (FH) Andreas Hoch)