Artimo Dhr. Raymond van Hal De Meeten 53 PB1150 4700 BD ROOSENDAAL Nederland



Your notice of 02-10-2017

Your reference

Date 03-11-2017

Analysis Report 17.05626.01

Required tests:

EN 13773 (2003)

Identification number	Information given by the client	Date of receipt
T1720805	Forssa IFR	02-10-2017

Gina Créelle

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T1720805 - Forssa IFR

<u>Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.</u>

Date of ending the test 16-10-2017

Standard used EN 1101 (1995) + A1 (2005)

Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

Ignition Bottom edge

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

Flame application	Cases of	Cases of		
time (s)	ignition	non-ignition		
1	0	1		
2	0	1		
3	0	1		
4	0	1		
5	0	1		
10	0	1		
15	0	1		
20	0	5		

The mean of the recorded times at which ignition was observed is calculated No ignition within 20 s

Width

Flame application	Cases of	Cases of		
time (s)	ignition	non-ignition		
1	0	1		
2	0	1		
3	0	1		
4	0	1		
5	0	1		
10	0	1		
15	0	1		
20	0	5		

The mean of the recorded times at which ignition was observed is calculated No ignition within $20\ \mathrm{s}$

Reference: T1720805 - Forssa IFR

<u>Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.</u>

Date of ending the test 02-11-2017

Standard used EN 13772 (2011) Product standard EN 13773 (2003)

Deviation from the standard

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Face A	Face B	Face A	Face A
Severance1st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	130	130	140	130
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face A	Face A
Severance1st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	135	130	130	130
Flaming debris	no	no	no	no

Classification in accordance with EN Class 1 13773

Performed under accreditation in the fire lab under the responsibility of Mieke Demeyer