Artimo Textiles
De Meeten 53
4706 NK Roosendaal
The Netherlands

ISO 17025
BELAC
056-TEST

Your notice of	Your reference	Date
13-08-2018		28-09-2018

Analysis Report 18.04624.05

Required tests :

EN 13773 (2003)

Identification number	Information given by the client	Date of receipt
T1818969		
Fosco		13-08-2018

Mieke Demeyer

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be
Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be

VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: **T1818969 - Fosco**

Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.

Date of ending the test	31-08-2018
Standard used	EN 1101 (1995) + A1 (2005)
Product standard	EN 13773 (2003)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Ignition	Bottom edge

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

No ignition within 20 s

Performed under accreditation in the fire lab under the responsibility of Mieke Demeyer

Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

No ignition within 20 s

Performed under accreditation in the fire lab under the responsibility of Mieke Demeyer

Reference: **T1818969 - Fosco**

Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 14-09-2018
Standard used EN 13772 (2011)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%
The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Face A	Face B	Face A	Face A
Severance 1st thread	no	no	no	no
Severance 2nd thread	no	no	no	no
Severance 3rd thread	no	no	no	no
Time to sever 3rd thread (s)	/	/	/	/
Destroyed length (mm)	160	135	145	150
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face A	Face A
Severance 1st thread	no	no	no	no
Severance 2nd thread	no	no	no	no
Severance 3rd thread	no	no	no	no
Time to sever 3rd thread (s)	/	/	/	/
Destroyed length (mm)	170	135	145	150
Flaming debris	no	no	no	no

Classification in accordance with EN 13773 **Class 1**

Performed under accreditation in the fire lab under the responsibility of Mieke Demeyer