

ARTIMO TEXTILES BV
DE MEETEN 53, 4706 NK ROOSENDAAL, NL

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)Woven fabric (FR B1/EN HERRINGBONE MEDIUM BLACKOUT)

Sample Color : (A)05

Composition : (A)100% Polyester

End Use : (A)CURTAIN AND DRAPERY

Style No. : PALLAS

Order No. : 3310


Sample Receiving Date : Aug 11, 2022

Testing Period : Aug 11, 2022 - Aug 24, 2022

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, for further details, please refer to the following page(s).

Test Performed : Selected test(s) as requested by applicant

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Hangzhou Branch



jack-yl_zhang(Account Executive)



SGS-CSTC Standards Technical Services Co., Ltd.
Hangzhou Branch Testing Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

3-6F, No.4 Building, Huayue Hi-Tech Zone, No.1180 Bin'an Road, Binjiang District, Hangzhou, Zhejiang, China 310052 t (86-571)86791199 f (86-571)87688901 www.sgsgroup.com.cn
中国·浙江·杭州·滨江区滨安路1180号华业高科技产业园4号楼3-6层 邮编: 310052 t (86-571)86791199 f (86-571)87688901 e sgs.china@sgs.com

Test Result

Textiles and Textile Products - Burning Behaviour - Curtains and Drapes - Classification Scheme[^]
(EN 13773:2003)

Sample: A

Detailed Procedure to Determine the Ignitability of Vertically Oriented Specimens (Small Flame)
(EN 1101:1995; EN ISO 6940:1995)

After 5 washes

Ignition time (s)	Lengthwise	Widthwise
1	N	N
2	N	N
3	N	N
4	N	N
5	N	N
10	N	N
15	N	N
20	N	N

Remark:

- (1) "Y" : Ignition ; "N" : Non-ignition
- (2) Ignition shall be deemed to have occurred if flaming of the specimen which gives an Afterflame time of 5s or more or which reaches the top or vertical edges in less than 5s.
- (3) Burner ignition location: Bottom edge ignition
- (4) Ignition time: 1-5s, 10s, 15s, 20s
- (5) Gas used: Propane

Cleansing procedure:

reduced washing procedure: automatic machines (type A) at 40°C, line dry

Textiles and textile products - Burning behaviour - Curtains and drapes - Measurement of flame spread of vertically oriented specimens with large ignition source
(EN 13772:2011)

After 5 washes

Specimen	Lengthwise			Widthwise		
	1	2	3	1	2	3
T1 severed (Y/N)	N	N	N	N	N	N
T3 severed (Y/N)	N	N	N	N	N	N
T1 (seconds)	/	/	/	/	/	/
T3 (seconds)	/	/	/	/	/	/
Flaming debris (Y/N)	N	N	N	N	N	N

Remark:

- (1) T1: From the start of the application of the igniting flame to the severance of the first marker thread (240mm)
- (2) T3: From the start of the application of the igniting flame to the severance of the third marker thread (540mm)
- (3) Y= Yes; N=No
- (4) Burner ignition location: Bottom edge ignition.
- (5) Ignition time: 10s.
- (6) Gas used: Propane



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Washing Procedure:

reduced washing procedure: automatic machines (type A) at 40°C, line dry

Classification for EN 13773:

Class	Ignitability	Flame spread
1	Non ignition according to EN 1101	1 st marker threads not severed, no flaming debris, according to EN 13772
2	Non ignition according to EN 1101	3 rd marker threads not severed, no flaming debris, according to EN 13772
3	Non ignition according to EN 1101	3 rd marker threads severed, and/or flaming debris, according to EN 13772
4	Ignition according to EN 1101	3 rd marker threads not severed, no flaming debris, according to EN 1102
5	Ignition according to EN 1101	3 rd marker threads severed, and/or flaming debris, according to EN 1102

Conclusion:

The submitted sample **complies** with the requirement of **Class 1** prescribed in EN 13773:2003 in "After Wash" states.

Remark: For EN 13772, This cleansing is suitable for fabrics treated with non-durable finishes. Fabrics treated with durable finishes, or are suitable for repeated cleansing shall be tested after 12 laundry cleansing

^This test was carried out by SGS Shanghai Laboratory

End of Report



SGS-CSTC Hangzhou Branch Textile Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

3-6F, No.4 Building, Huayue Hi-Tech Zone, No.1180, Bin'an Road, Binjiang District, Hangzhou, Zhejiang, China 310052 t (86-571)86791199 f (86-571)87688901 www.sgs.com.cn
 中国·浙江·杭州·滨江区滨安路1180号华业高科技产业园4号楼3-6层 邮编: 310052 t (86-571)86791199 f (86-571)87688901 e sgs.china@sgs.com